

Declaration of Performance
(according to regulation EU No 305/2011)

No. LPE Section S355J2

Section S355J2 / 1.0577 according EN 10025-2

To be used in-welded, bolted and riveted structures

Tata Steel UK Limited
Long Products Europe
PO Box 1, Brigg Road
Scunthorpe, DN16 1BP
Tel: +44 (0)1724 404040
Website : www.tatasteeleurope.com

CE Marking Notified Body
Lloyds Register Verification Limited
71 Fenchurch Street, London, EC3M 4BS
Tel :+44 (0)207 423 2428
Email : ecdirectives@lr.org
Website : www.lr.org

System of assessment and verification of constancy of performance of the product
System 2+


Notified factory production control certification body No. 0038 performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control



Jon Bolton – Director, Long Products Europe
Tata Steel UK Limited

1st July 2013
Date

Essential characteristic	Performance		Harmonised technical specification			
Tolerances on dimensions and shape	I & H Sections Equal Flange Tee Equal Angle Unequal Angle Tapered Flange I Bulb Flats	EN 10034 EN 10055 EN 10056-1 EN10056-2 EN 10024 EN 10067	EN10025-1 2004			
Yield strength (transverse)	Nominal thickness (mm)	Values Min (MPa)				
	>	<=				
	-	16			355	
	16	40			345	
	40	63			325	
	63	80			325	
	80	100			315	
100	150	295				
Tensile strength (transverse)	Nominal thickness (mm)	Values (MPa)			min	max
	>	<=				
	5	100	470	630		
	100	150	450	600		
Elongation (transverse)	Nominal thickness (mm)	Values min (% , 5.65√s ₀)				
	>	<=				
	5	40	20			
	40	63	19			
	63	100	18			
100	150	18				
Impact strength (longitudinal)	J2	27J at - 20°C				
Weldability CEV	Nominal thickness (mm)	Values max (%)				
	>	<=				
	-	30	0.45			
	30	40	0.47			
40	150	0.47				
Durability	Nominal thickness (mm)	Values max (%)				
	-	<=40	C:0,20 (>30mm 0,22) Si: 0,55 Mn: 1,60 P: 0,025 S: 0,025 Cu: 0,55			
	>40	150	C:0,22 Si: 0,55 Mn: 1,60 P: 0,025 S: 0,025 Cu: 0,55			



0038

Tata Steel
Long Products Europe
PO Box 1, Brigg Road
Scunthorpe, UK

13

LPE Section S355J2

EN 10025-1 – 2004

Section S355J2 / 1.0577

To be used in-welded, bolted and riveted structures

Elongation :
Tensile Strength :
Yield Strength : EN10025-2
Impact Strength :
Weldability :
Durability :

Dangerous Substances : No Performance Determined